CP/TF/01

# TEST REPORT ON BITUMEN

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2017-06-14-09** **Date: 16-06-17** |
| **Customer** | : | Assistant Executive Engineer, Byatarayanapura Sub division, BBMP, Bangalore. |
| **Address** | : | Byatarayanapura Sub division, BBMP, Bangalore. |
| **Project Name** | : | Resurfacing of the roads in Bhagyashree layout in Ward no.06 Byatarayanapura Sub division. |
| **Agency** | : | Sri. R. Nataraj, Contractor, #860, 19th cross, 5th block, HMT layout, Vidyaranyapura, Bangalore-97 |
| **Customer's Reference** | : | EE/BTP/BBMP/E-PMT/67/2014-15 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 14-06-17 |
| **Sample ID No** | : | 2017-06-14-09/01 |
| **Sample Type** | : | Bitumen |
| **Reference to BIS codes** | : | IS: 1201-1220(1978) (Reaffirmed-2004) |
| **Date of test** | : | 15-06-17 |

## Test Results

| Sl.no | Name of Test | Result | Requirements as per IS:73-2013 |
|---|---|---|---|
| 1 | Penetration at 25°C , in 1/10th mm | **67** | 60 to 70 |
| 2 | Softening Point, °C | **49.4** | Min. 40°C |
| 3 | Ductility, cm | **93** | Min. 75cm |
| 4 | Flash point, °C | **228** | Min. 220°C |
| | Fire point, °C | **242** | |

**Note:**
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

**FOR CIVIL Pro.**

**R KARTHIK RECHAN**
Authorized Signatory
**Quality Manager**


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com